



Breplasta®

Fassaden Handspachtel Leicht

Ready-mixed filler for exterior use



Product information

Grey ready-mixed hand filler for minor repairs outdoors. Can also be used indoors on mineral surfaces. The special consistency combined with high build, good adhesive and low tension means that the filler has excellent working properties. Filler should be applied on clean, dry surfaces at a minimum temperature of +10°C. The product is suitable for initial filling and thin smoothing.

The product fulfills CE marking requirements according to EN 15824 and is manufactured in accordance with ISO 9001 and ISO 14001.

Tools are to be cleaned in water. Large volumes of waste can be deposited as normal refuse at municipal refuse facilities. The plastic in the packaging is recyclable and must therefore be taken to the appropriate recycling point or municipal recycling plant.

Instructions

Apply by hand on clean, dry and firmly attached surfaces at a minimum temperature of +10°C. Eye protection and a dust mask are recommended when sanding. Dust off before the next treatment. Filled surfaces should be primed before wallpapering.

Eye protection and a dust mask are recommended when sanding. Dust off before the next treatment. Filled surfaces should be primed before wallpapering.

Consumption of material

1 mm thin coat plastering = approx. 1 litre/m².

Drying time

The drying time is dependent on substrate, layer thickness, temperature, air humidity etc.

Storage

Protect from frost and direct sunlight. Filler is perishable and therefore labelled with a date of production. Unopened packs can be stored for 12 months.



Technical data

Binder: Latex co-polymer

Solvent: Water

Filler: Microspheres and white dolomite

Particle size: Max: 0.2 mm

pH: Approx.: 9

Colour: Grey

Flammability: Does not spread or support fire

Breplasta product data sheets are provided for guidance only. The data presented does not constitute a guarantee that the product will have certain properties or be suitable for a particular area of application. These values apply under normal circumstances. We reserve the right to make changes without prior notice. Users are responsible for ensuring they use the latest edition of this data sheet. Checks can be made at www.dalapro.com.

Last updated 8 March 2022